


OPOFFERINGSANODEN - ZINK



Anode Ref.	L1 (mm)	L2 (mm)	W1 (mm)	W2 (mm)	T (mm)	HC (mm)	Netto gewicht (Kg)	Bruto gewicht (Kg)
ATZN 036	200	190	100	90	30	110	3.5	3.6
ATZN 073	300	292	150	142	25	160	7.0	7.3
ATZN 083	300	282	150	132	31	160	8.0	8.3
ATZN 120	300	290	150	140	43	160	11.7	12.0

Kenmerken:

- Open circuit potentiaal: 0.95V (Ag/AgCl referentie electrode).
- Capaciteit: 780 Amp. Hr/Kg.
- Verbruik: 11.25 Kg/Amp. Yr.

Chemische samenstelling:

Al%	Cd%	Pb%	Fe%	Cu%	Si%	Zn%
0.1-0.5%	0.025-0.15%	0.006% max.	0.005% max.	0.005% max.	0.125% max.	Rest