


OPOFFERINGSANODEN - ZINK



Anode Ref.	A (mm)	L1 (mm)	L2 (mm)	W1 (mm)	W2 (mm)	T (mm)	Cw (mm)	Ct (mm)	Netto gewicht (Kg)	Bruto gewicht (Kg)
ATZN 035	300	200	140	97	75	33	25	8	3.2	3.7
ATZN 078	350	265	125	150	125	35	40	8	7.1	8.0
ATZN 130	530	390	285	155	130	35	40	8	12.0	13.3
ATZN 286	650	550	470	135	115	65	40	8	27.0	29.0

Kenmerken:

- Open circuit potentiaal: 0.95V (Ag/AgCl referentie electrode).
- Capaciteit: 780 Amp. Hr/Kg.
- Verbruik: 11.25 Kg/Amp. Yr.

Chemische samenstelling:

Al%	Cd%	Pb%	Fe%	Cu%	Si%	Zn%
0.1-0.5%	0.025-0.15%	0.006% max.	0.005% max.	0.005% max.	0.125% max.	Rest