

MAGNESIUM ANODEN



Anode Ref.	Netto gewicht (Kg)	Bruto gewicht incl. backfill (Kg)	Open circuit potentiaal (V)
AT 50	5.0	14.0	1.55
AT 77	7.7	16.0	1.55
AT 100	10.0	22.0	1.55

Chemische samenstelling:

Al%	Mu%	Cu%	Fe%	Zn%	Si%	Ni%	Andere%	Mg
5.30-6.70	0.15-0.17	0.05	0.005	2.50-3.50	0.30	0.003	0.30	Rest

Chemische samenstelling backfill:

- Gipspoeder 75%
- Betonite poeder 20%
- Sodium sulfaat 5%